Pyrolon® Plus 2

Perfect for use over thermally protective and

arc protective clothing!

From coveralls to lab coats to dosimeter stripped nuclear wear, disposable clothing of Pyrolon® Plus 2 come with all the essential features, distinct advantages and assurances of protection that only quality design and materials can deliver.

- Second generation Pyrolon® Plus 2 offers wet or dry strength superior to that provided by other traditional Flame Resistant disposables
- Meets the NFPA 2113 requirements for section 5.1.9.
- Pyrolon® Plus 2 is breathable, making this a cool and comfortable garment to wear.

Pyrolon® Plus 2 can be used in work environments where hazardous or non-hazardous contaminants may be present. Pyrolon® Plus 2 quality standards meet ANSI/ISEA 101.

> Wear Pyrolon® Plus 2 over expensive thermally protective and arc protective clothing!

















Labcoat 07101

- Snap closure
- 2 pockets
- Long sleeve


Sizes: S − 5X Case Pack: 30



Labcoat 07140

- Snap closure
- No pockets
- · Long sleeves. Sizes: S – 5X

Case Pack: 30



Shirt 07201

- Snap closure
- Long sleeves

Sizes: S - 5XCase Pack: 50



Pants 07301

 Elastic waist Sizes: S – 5X

Case Pack: 50

Coverall 07412 Zipper closure

Case Pack: 25

 Zipper closure Sizes: S - 5X · Attached hood

 Boots Elastic wrists

Coverall

07414

Sizes: S - 5XCase Pack: 25




Coverall 07417

- Zipper closure
- Elastic wrists
- Elastic ankles

Sizes: S – 5X

Case Pack: 25




Coverall 07428

- Zipper closure
- · Attached hood
- Elastic wrists

• Elastic ankles Sizes: S – 5X

Case Pack: 25



Blue Boot Cover 07903B

- Elastic top • 17" high
- Sizes: S/M, L/XL, 2X Case Pack: 200 pair



Blue Bell Shaped Hood 07903B

- Elastic face
- Covers shoulders One size
- Case Pack: 200 pair



All Pyrolon® Plus 2 garments are available in White or Blue. For Blue, add a "B" at the end of the style number.

Pyrolon® Plus 2 Physical Properties

Physical Property	Test Method	Units	Test Results
Basis Weight	ASTM D3776	oz/y ²	2.4 oz/y ²
Grab Tensile MD	ASTM D5034	lbs.	31.0 lbs.
Grab Tensile XD	ASTM D5034	lbs.	20.0 lbs.
Trapezoidal Tear MD	ASTM D5733	lbs.	4.5 lbs.
Trapezoidal Tear CD	ASTM D5733	lbs.	5.6 lbs.
Air Permeability	ASTM D737	cfm	52 cfm
Char Length MD	ASTM D6413	inches	3.70 inches
Char Length XD	ASTM D6413	inches	3.70 inches
Ignition Point	ı	degrees F	1000° F
Charge Decay	NFPA 99		Pass

Do not use for fire protection. Avoid open flame or intense heat. Pyrolon® Plus 2 garments are not washable. Washing removes the special finishes, thereby removing the flame retardancy, water and oil repellent characteristics.



800-645-9291 | 256-350-3873 Email: info@lakeland.com

www.lakeland.com